

# Wired— Ultrafabrics®

Wired expresses how touch and color are interwoven. Its unique appeal encourages tactile interaction and emotional connections to the physical world and must be felt to be believed. A layering of color provides depth of design, while parallel and perpendicular lines create a sense of movement. A palette combining twelve fresh and timeless hues offer wide-ranging design possibilities.

## Distinctive Features

- Superior durability — industry-leading 14+ weeks hydrolysis results
- Blends backcloth for expanded upholstery capabilities
- Bleach cleanable (1:5 bleach/water solution)



# Wired— Ultrafabrics®

## Specifications

### Description

Ultratech™ Wired

### Composition

Proprietary FR treatment, 100% Polycarbonate Polyester Surface, 65% Polyester, 35% Rayon Backing

### General

- Roll Size: 33 yards (+/- 10%)
- Width: 54” (+/- 10%)
- Weight: 12.5 oz/sq yd /426 g/sm (+/- 10%)
- Thickness: 1.27 mm / .05” (+/- 10%)
- Stretch Percent: 5% Warp, 25% Fill
- Set Percent: 2% Warp, 6% Fill

## ULWIFR Meets:

| Test                         | Method  |
|------------------------------|---|
| 60 second Vertical Burn Test | FAR 25.853(a) Appendix F, Part I,(a), 1(i):60sec  |
| 12 Second Vertical Burn      | FAR 25.853(a) Appendix F, Part I,(a), 1(ii):12sec |
| Seat Cushion with Fireblock  | FAR 25.853 (b) Appendix F, Part II                |
| Abrasion Test                | ASTM D4157 Wyzenbeek method 400,000 double rubs   |
| Breaking Force               | ASTM D5034: Warp- 75 min, Fill- 70 min            |
| Colorfastness to Light       | AATCC 16.3, 200 hours Grade 4-5                   |
| Colorfastness to Crocking    | AATCC 8: Grade 5                                  |